

705 PO

Elasticity and Flexibility Modifier

Supplied in shape of:

Mixture, Pellets.

Active agent:

Polyolefin plastomer.

Area of use:

HECO[®]ELAST 705 PO is suitable for processing polyolefins such as polyethylene and polypropylene in injection moulding, extrusion and extrusion blow moulding.

Recommended dose:

HECO[®]ELAST 705 PO is added in the range of 5.0 - 25.0 % depending on the desired properties.

Properties:

HECO[®]ELAST 705 PO significantly improves the elasticity and flexibility of polyolefins. In addition, it also improves the flow properties and transparency.

Gebindegrösse:

1.375,0 kg (55 Sack à 25,0 kg) / Palette, netto.

Safety Precautions

Foodstuff regulation:

Approval according to EU (Regulation) No. 10/2011.

Approval according to the US FDA, see "Food Contact Approvals".

Storage:

No reduction in quality has been reported when properly stored under normal room conditions up to twelve (12) months.

Handling:

The precautions and hygienic measures usual in the handling of any chemical product should be observed.

In case of fire:

In case of fire, suitable extinguishers are aqueous spray, foam or dry chemical; a full jet of water is unsuitable.

HECOPLAST[®] and **HECO[®]** are registered trademarks

Our information is based on the most careful analysis, nevertheless these are not guaranteed product features.
Specific field tests are being recommended under any circumstance.

HECOPLAST[®] GmbH Kunststoffadditive, Zollhausstrasse 24, D - 58640 Iserlohn Telephone + 49 2371 / 797 61-0 – E-Mail: info@hecoplast.de