

706 PO

Film Modifier

Supplied in shape of:

Mixture, Pellets.

Active agent:

Thermoplastic polyolefin.

Area of use:

HECO[®]ELAST 706 PO is suitable for processing polyethylene in extrusion blow moulding.

Recommended dose:

HECO[®]ELAST 706 PO is added in the range of 1.0 - 30.0 % depending on the desired properties.

Properties:

HECO[®]ELAST 706 PO is characterised by a very high softness and a very low modulus. It does not contain any slip agents or anti-blocking agents. It is used for the production of soft hygiene films and heavy duty films as well as for the modification of LDPE or LLDPE to increase mechanical properties and puncture resistance.

Pallet size:

1.375.0 kg (55 sacks at 25.0 kg) / pallet, net.

Safety Precautions

Foodstuff regulation:

Approval according to EU (VO) No. 10/2011. This product contains one or more components with a specific migration limit.

Approval according to the US FDA, see "Food Contact Approvals".

Storage:

No reduction in quality has been reported when properly stored under normal room conditions up to twelve (12) months.

Handling:

The precautions and hygienic measures usual in the handling of any chemical product should be observed.

In case of fire:

In case of fire, suitable extinguishers are aqueous spray, foam or dry chemical; a full jet of water is unsuitable.

HECOPLAST[®] and **HECO[®]** are registered trademarks

Our information is based on the most careful analysis, nevertheless these are not guaranteed product features.
Specific field tests are being recommended under any circumstance.

HECOPLAST[®] GmbH Kunststoffadditive, Zollhausstrasse 24, D - 58640 Iserlohn Telephone + 49 2371 / 797 61-0 – E-Mail: info@hecoplast.de