

# HECO®NUK 425PE

# **Nucleating and Demoulding Agent**

# Supplied in shape of:

Mixture, Granule.

#### Active agent:

Nucleating and demoulding agent on a polyethylene carrier.

#### Area of use:

**HECO**<sup>®</sup>NUK 425 PE is suitable for processing polyolefins such as polyethylene and polypropylene, as well as polyamides in injection moulding and extrusion.

#### **Recommended dose:**

 $\rm HECO^{\$}NUK$  425 PE is added in the range of 1.5 – 2.5 % depending on the desired properties.

#### **Properties:**

**HECO**<sup>®</sup>NUK 425 PE improves the mechanical strength, impact strength, heat resistance, crystallisation temperature and opacity of the processable plastic. It can improve the output rate of the production plant by 8 to 15%. It contains a slip agent, which facilitates and speeds up the de moulding process, decreases cycle times and reduces stress whitening leading to a lower scrap rate.

#### Pallet size:

1.000.0 kg (50 sacks at 20.0 kg) / pallet, net.

# Safety Precautions

# Foodstuff regulation:

Approval according to EU (VO) No. 10/2011. Specific migration limit: 60 mg/kg food (10 mg/dm<sup>2</sup>). In accordance with European Pharmacopoeia 11th edition 2023.

#### Storage:

No reduction in quality has been reported when properly stored under normal room conditions up to twelve (12) months.

#### Handling:

The precautions and hygienic measures usual in the handling of any chemical product should be observed.

#### In case of fire:

In case of fire, suitable extinguishers are aqueous spray, foam or dry chemical; a full jet of water is unsuitable.

### **HECOPLAST<sup>®</sup>** and **HECO<sup>®</sup>** are registered trademarks

Our information is based on the most careful analysis, nevertheless these are not guaranteed product features. Specific field tests are being recommended under any circumstance.

HECOPLAST<sup>®</sup> GmbH Kunststoffadditive, Zollhausstrasse 24, D - 58640 Iserlohn Telephone + 49 2371 / 797 61-0 – E-Mail: info@hecoplast.de