



# P Slip and Anti-blocking Agent in PP

## Supplied in shape of:

Mixture, Granule.

### **Active agent:**

Slip and anti-blocking agent on a polypropylene carrier.

#### Area of use:

**HECO**®SLIP 114 PP is suitable for processing polypropylene in injection moulding and extrusion.

#### **Recommended use:**

**HECO**®SLIP 114 PP is added in the range of 1.5 - 4.0 % depending on the desired properties. We recommend an addition of at least 1.5 - 2.5 %.

## **Properties:**

**HECO**®SLIP 114 PP is an external slip agent reducing friction and adhesion of the mixture during the mixing process. It migrates to the surface slowly and forms a durable oleaginous layer with good slip and anti-blocking properties.

#### Pallet size:

1000.0 kg (50 sacks at 20.0 kg) / pallet, net.

# **Safety Precautions**

## **Foodstuff regulation:**

Approval according to EU (VO) No. 10/2011.

Specific migration limit: 60 mg/kg food (10 mg/dm²).

Approval according to the US FDA, see "Food Contact Approvals".

In accordance with European Pharmacopoeia 11th edition 2023.

# Storage:

No reduction in quality has been reported when properly stored under normal room conditions up to twelve (12) months.

# **Handling:**

The precautions and hygienic measures usual in the handling of any chemical product should be observed.

#### In case of fire:

In case of fire, suitable extinguishers are aqueous spray, foam or dry chemical; a full jet of water is unsuitable.

**HECOPLAST**<sup>®</sup> and **HECO**<sup>®</sup> are registered trademarks

Our information is based on the most careful analysis, nevertheless these are not guaranteed product features.

Specific field tests are being recommended under any circumstance.