

123 PP

Slip Additive in PP

Supplied in shape of:

Mixture, Granule.

Active agent:

Slip agent with nucleation aid on a polypropylene carrier.

Area of use:

HECO®SLIP 123 PP is suitable for processing polypropylene in injection moulding and extrusion.

Recommended dose:

HECO®SLIP 123 PP is added in the range of 1.0 – 3.0 % depending on the desired properties. We recommend an addition of at least 1.0 – 2.0 %.

Properties:

HECO®SLIP 123 PP is an external slip agent. It prevents the build-up of colour pigment deposits/residue up into the dead zones. It acts as a form stabiliser and helps to prevent sink marks when demoulded at the right kick-off temperature.

Pallet size:

1000.0 kg (50 sacks at 20.0 kg) / pallet, net.

Safety Precautions

Foodstuff regulation:

Approval according to EU (VO) No. 10/2011.

Approval according to the US FDA, see "Food Contact Approvals".

Storage:

No reduction in quality has been reported when properly stored under normal room conditions up to twelve (12) months.

Handling:

The precautions and hygienic measures usual in the handling of any chemical product should be observed.

In case of fire:

In case of fire, suitable extinguishers are aqueous spray, foam or dry chemical; a full jet of water is unsuitable.

HECOPLAST® and **HECO®** are registered trademarks

Our information is based on the most careful analysis, nevertheless these are not guaranteed product features.
Specific field tests are being recommended under any circumstance.

HECOPLAST® GmbH Kunststoffadditive, Zollhausstrasse 24, D - 58640 Iserlohn Telephone + 49 2371 / 797 61-0 – E-Mail: info@hecoplast.de