



# 224 P

## Short-/long-term antistatic

## Supplied in shape of:

Mixture, Granule.

#### **Active agent:**

Combination of short- and long-term antistatic agents on a polypropylene carrier.

#### Area of use:

**HECO®** STAT 224 PP is suitable for processing polypropylene in film production and injection moulding applications.

#### **Recommended dose:**

**HECO**®STAT 224 PP is added in the range of 1.0 - 1.5 % in films and 1.0 - 3.0 % in injection moulding, depending on the desired properties.

#### **Properties:**

**HECO®**STAT 224 PP is a combination of a short- and long-term antistatic agent. The short-term antistatic agent migrates immediately to the surface, whereby the formed film dissipates the charges directly. The long-term antistatic agent forms a self-organising, dynamic and ordered structure, which in turn continues to dissipate the static charge even after the short-term antistatic agent has been used up.

#### Pallet size:

1.000.0kg (50 sacks at 20.0kg) / pallet, net..

# **Safety Precautions**

### **Foodstuff regulations:**

Approval according to EU (VO) No. 10/2011. Specific migration limit: 1.2 mg/kg food. Approval according to the US FDA, see "Food Contact Approvals".

#### Storage

No reduction in quality has been reported when properly stored under normal room conditions up to twelve (12) months.

# Handling:

The precautions and hygienic measures usual in the handling of any chemical product should be observed.

# In case of fire:

In case of fire, suitable extinguishers are aqueous spray, foam or dry chemical; a full jet of water and  $CO_2$  are unsuitable.

**HECOPLAST**<sup>®</sup> and **HECO**<sup>®</sup> are registered trademarks

Our information is based on the most careful analysis, nevertheless these are not guaranteed product features. Specific field tests are being recommended under any circumstance.